

Kromasil 100 Å

SIL, C4, C8, C18, NH2 and Phenyl

High performance spherical silica for analytical to process scale liquid chromatography. Functionalized Kromasil 100 Å is manufactured using monofunctional silanes, and is fully end-capped (*). This gives high reproducibility and chemical stability.

Product Characteristics

Particle sizes:**

2.5 μm, 3.5 μm, 5 μm, 7 μm, 10 μm, 13 μm, 16 μm

Particle size distribution:

(Coulter Multisizer)

dp [µm]	dp90/dp10
10, 13, 16	< 1.70
7	< 1.60
5	< 1.55
3.5	< 1.45
2,5	< 1.40

Spec surface area:

320 m²/g (multi-point BET)

Pore volume:

0.9 ml/g (N2-adsorption)

Pore size:

110 Å (N2-adsorption)

Pore size distribution:

80% ± 25 Å (N2-adsorption)

97% of the BET-surface is accessible for toluene

Coverage:

(elemental analysis)

C4: 8% C, $3.8 \, \mu mol/m^2$ C8: 12% C, $3.7 \, \mu mol/m^2$ C18: 20% C, $3.5 \, \mu mol/m^2$ NH2: 1.7% N, $4.5 \, \mu mol/m^2$ Phenyl: 14% C, $3.7 \, \mu mol/m^2$

Chemical purity:

Typical figures (AAS or ICP):

Na: < 10 ppm Al: < 5 ppm Fe: < 5 ppm

Chemical stability:***

Kromasil derivatized phases are stable between pH 1.5 and 10 and as high as 12 under certain conditions.

Mechanical stability:

Allows repeated packing at up to 700 bar (10 000 psi)

Packed density:

SIL: 0.50 g/ml C4: 0.57 g/ml C8: 0.60 g/ml C18: 0.66 g/ml NH2: 0.53 g/ml Phenyl: 0.59 g/ml


Delivery

Kromasil bulk is delivered in polyethylene bottles or in polyethylene bags packed in plastic drums.

Kromasil, patented by Akzo Nobel Pulp and Performance Chemicals AB, is manufactured in multi-kilogram batches with high reproducibility.

The development, production and marketing of Kromasil are ISO 9001 certified.

- *) Kromasil NH2 is derivatized using a trifunctional silane, and is not end-capped.
- **) Kromasil Phenyl is available in 5 μ m, 10 μ m and 16 μ m particle size.
- ***) Applies to derivatized phases except NH2.



AUTHORIZED DISTRIBUTOR

MZ-Analysentechnik GmbH, Barcelona-Allee 17• D-55129 Mainz Tel +49 6131 880 96-0, Fax +49 6131 880 96-20 e-mail: info@mz-at.de, www.mz-at.de